

XP-002349112

(C) WPI / DERWENT

AN - 2001-592724 [67]

AP - JP20000017547 20000126

CPY - SAKB

DC - G01

DR - 1521-U 1531-U 1966-U

FS - CPI

IC - B01J2/00 ; C01F7/02 ; C09C1/02 ; C09C1/40 ; C09C3/06 ; C09D5/36 ;  
C09D201/00

MC - G01-A01

PA - (SAKB ) OTSUKA KAGAKU YAKUHHN KK

PN - JP2001207077-A 20010731 DW200167 C09C1/02 004pp

PR - JP20000017547 20000126

XA - C2001-175942

XIC - B01J-002/00 ; C01F-007/02 ; C09C-001/02 ; C09C-001/40 ; C09C-003/06 ;  
C09D-005/36 ; C09D-201/00

AB - JP2001207077 NOVELTY - The pearly luster pigment consists of an alkali metal or an alkaline earth metal containing tabular boehmite, coated with a metallic oxide. The alkali metal is sodium or potassium and alkaline earth metal is calcium, strontium or barium. The metallic oxide is titanium oxide, zirconium oxide, tin oxide and/or hydrated compounds.

- USE - As pearly luster pigment.

- ADVANTAGE - The pearly luster pigment has excellent glossiness, high-temperature heat resistance and mechanical strength. The pigment has uniform thickness and high average aspect ratio. The pigment is colorless and transparent, and has minimum sedimentation property.

- (Dwg.0/0)

IW - PEARL PIGMENT CONSIST ALKALI METAL ALKALINE EARTH METAL CONTAIN  
TABULAR BOEHMITE COATING METALLIC OXIDE

IKW - PEARL PIGMENT CONSIST ALKALI METAL ALKALINE EARTH METAL CONTAIN  
TABULAR BOEHMITE COATING METALLIC OXIDE

NC - 001

OPD - 2000-01-26

ORD - 2001-07-31

PAW - (SAKB ) OTSUKA KAGAKU YAKUHHN KK

TI - Pearly luster pigment consists of alkali metal or alkaline earth metal containing tabular boehmite, coated with metallic oxide